

Oligomers for LED-Curable Nail Gel Coatings



Formulate nail gel coatings that look salon-fresh longer

Overcome common nail coating issues like low gloss, color drift, regulatory compliance issues, premature chipping, and high heat generation during cure by formulating your nail gel coatings with a Bomar® oligomer. Coatings formulated with Bomar oligomers have a non-yellowing, high-gloss finish for vibrant coatings, and exhibit excellent durability for a longer lasting salon-fresh look. They generate minimal heat during LED cure, are easily removed with acetone, and are created with low MeHQ levels for insignificant skin irritation. Our oligomers for nail gel coatings are INCI registered and meet many global regulatory conditions.

Bomar oligomers are ideally suited for top coat, color coat, or base coat LED-curable nail gel polishes sold in professional salons or do-it-at-home kits. They cover a diverse range of mechanical properties allowing complete formulation flexibility, enabling formulators to get the desired coating properties.

If one of our existing oligomers do not provide the desired properties for your application, Bomar can work with you to develop a custom oligomer. We also offer contract manufacturing services for companies that would like to outsource synthesis.

- Low heat generation to eliminate skin irritation during cure
- Diverse mechanical properties for formulation flexibility
- Non-yellowing, high-gloss finish for vibrant coatings
- Easy removal with acetone
- Excellent durability for nails that stay salon fresh longer
- INCI registered oligomers

AVAILABLE PRODUCTS

Bomar recommends BR-952, BR-541S, BRC-443D, BR-742M, BR-744BT, and XR-741MS for LED-curing nail gel coating applications. The table below lists properties that formulators may want to control during nail coating formulation. For more information on these products, please visit our website.



Product	Viscosity (cP) ASTM D4287	Durometer Hardness (D) ASTM D2240	Gloss ASTM D2457	Yellowness (b*) ASTM E1164	Rolling Ball Tackiness Tester (cm) ASTM D3121	Glass Transition Temperature (°C) ASTM E831	Maximum Temp. Evolved During LED-Curing (°C)	200Acetone Double Rub Resistance ASTM D4572
BR-541S	7,100	D65	78	0.005	85	44	45	80
BR-742M	58,000	D77	83	0.26	48	65	36	50
BR-744BT	75,000	D51	67	0.33	10	-18	36	20
BR-952	1,100	D78	85	0.2	44	159	52	200
BRC-443D	49,000	D64	76	0.26	45	41	40	50
XR-741MS	92,000	D86	74	0.04	100	110	39	200
BRC-843D	13,000	D60	83	0.14	82	45	42	57

Global Headquarters: 51 Greenwoods Road | Torrington, CT 06790 | USA | +1 860-626-7006

www.bomar-chem.com

© 2015–2022 Bomar. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Bomar.

Technical data provided is of a general nature and is based on laboratory test conditions. Bomar does not warrant the data contained in this document. Any warranty applicable to the product is strictly limited to that contained in Bomar's standard Conditions of Sale. Bomar does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this document shall act as a representation that the product use or application will not infringe a patent owned by someone other than Bomar or act as a grant of license under any Bomar Patent. Bomar recommends that each user adequately test its proposed use and application before actual repetitive use. BSS001 12/7/2021